

				Moisture Content %	Loss on Ignition %	Sulfuric Anhydride %	Total Silica %	Surface Area m ² /g	Available Alkalis %	Total Alkalai	Chloride Ion %	Relative Strength % 7daysAcc.	Relative Density	Relative Testing Cement	Bulk Density Kg/M ³	Fineness	Fineness Index	
Registration	Date Sampled	Sample Number												Boral				
ATIC 128	Jan-18	199905		0.4	2	1.8	98	18.331	0.2		0.006	116	2.26	Berrima SL	602			
ATIC 128	Feb-18	201097		0.5	1.8	1.4	98.1	17.7006	0.1		0.008	108	2.24	Berrima SL	629			
ATIC 128	Mar-18	201328		0.7	1.9	1.1	97.2	17.8861	0.01		0.008	109	2.23	Berrima SL	638			
ATIC 128	Apr-18	201098		0.4	2.8	1.7	96.3	21.7855	0.1		0.008	124	2.23	Berrima SL	616			
ATIC 128	May-18	206469		0.7	1.9	0.1	94.4	17.7243	0.1		0.011	118	2.2	Berrima SL	698			
ATIC 128	Jun-18	207505		0.7	1.8	0.8	95.2	17.5391	0.1		0.015	106	2.21	Berrima SL	698			
ATIC 128	Jul-18	208067		0.7	1.7	0.9	94.2	17.7312	0.2		0.003	121	2.21	Berrima SL	685			
ATIC 128	Aug-18	208680		0.7	2.4	1.2	95.8	17.9714	0.2		0.0053	118	2.2	Berrima SL	651			
ATIC 128	Sep-18	210057		0.9	1.7	0.7	96.2	17.8309	0.1		0.026	121	2.22	Berrima SL	646			
ATIC 128	Oct-18	212126		0.9	1.9	0.8	95.2	17.5196	0.2		0.002	128	2.21	Berrima SL	641			
ATIC 128	Nov-18	214368		0.8	2	0.3	94.7	18.5695	0.1		0.002	118	2.2	Berrima SL	636			
	Dec-18	215236		1	2	0.2	97.7	14.5828	0.1	2.5	0.013	106	2.2	Berrima SL	643			